



Protective & Marine Coatings

ZINC CLAD® III HS ORGANIC ZINC-RICH EPOXY PRIMER

PART A	B69A100	GRAY-GREEN, BASE
PART A	B69LW100	OAP BLUE, BASE
PART B	B69V100	HARDENER
PART F	B69D11	ZINC DUST

Revised: August 04, 2016

PRODUCT INFORMATION

6.07

PRODUCT DESCRIPTION

ZINC CLAD III HS is a three-component, polyamide epoxy, zinc-rich coating. It has a low VOC level and contains 90.5% by weight of zinc dust pigment in its dried film.

- Meets Class B requirements for Slip Coefficient and Creep Resistance
- Provides cathodic protection
- Damaged film exhibits "self-healing" properties
- Fast Recoat Time
- Outstanding application properties

PRODUCT CHARACTERISTICS

Finish:	Flat
Color:	Gray-Green, OAP Blue
Volume Solids:	70% ± 2%, ASTM D2697
Weight Solids:	90% ± 2%, mixed
VOC (EPA Method 24):	Unreduced: <340 g/L; 2.80 lb/gal mixed Reduced 5%: <360 g/L; 3.00 lb/gal
Zinc Dust Pigment Content in Dry Film:	ASTM D 521 90% Min ASTM D 6580 85% Min
Mix Ratio:	3 components, premeasured 3.25 gallons (12.3L) total

Recommended Spreading Rate per coat:

	Minimum	Maximum
Wet mils (microns)	4.5 (113)	7.0 (175)
Dry mils (microns)	3.0 (75)	5.0 (125)
~Coverage sq ft/gal (m ² /L)	224 (5.5)	370 (9.1)
Theoretical coverage sq ft/gal (m ² /L) @ 1 mil / 25 microns dft	1120 (27.5)	

NOTE Brush or roll application may require multiple coats to achieve maximum film thickness and uniformity of appearance.

Drying Schedule @ 5.0 mils wet (125 microns):

@ 35°F/1.7°C @ 77°F/25°C @ 120°F/49°C

50% RH

To touch:	45 minutes	30 minutes	10 minutes
To handle:	2 hours	1 hour	30 minutes
To recoat*:			
minimum:	4 hours	30 minutes	30 minutes
**maximum:	none	none	none
To cure:	10 days	7 days	7 days

Drying time is temperature, humidity, and film thickness dependent

NOTE: Film must be free of solvent, hard and firm. When rubbed with the face of a coin or knife the film should polish but not flake or chip.

***Maximum Recoat: Unlimited. Must have a clean, dry surface for top-coating. "Loose" chalk or salts must be removed in accordance with good painting practice.*

Paint temperature must be at least 40°F (4.5°C) minimum.

Pot Life: 6 hours 4 hours 2 hours

Sweat-in-Time: 1 hour 30 minutes 15 minutes

Shelf Life:
Part A*: 18 months, unopened
Part B: 18 months, unopened
Part F: 24 months, unopened
Store indoors at 40°F (4.5°C) to 100°F (38°C)

*B69LW100 (Part A) has a 12 month shelf life

PRODUCT CHARACTERISTICS (CONT'D)

Flash Point:	67°F (19°C), Closed Cup, mixed
Reducer/Clean Up: Below 80°F (27°C):	Reducer #58 or MEK, R6K10
Above 80°F (27°C):	Reducer #58 or R7K104

RECOMMENDED USES

For use over properly prepared blasted steel.

- Fabrication Shops
- Bridge and Highway Structures
- Stadiums and Sports Complexes
- Drilling Rigs
- Piping
- Refineries
- Barges and Ships
- Wind Towers - onshore and offshore
- Shop or Field Applications
- Not recommended for immersion service
- Approved with FIRETEX hydrocarbon coatings

PERFORMANCE CHARACTERISTICS

Substrate*: Steel

Surface Preparation*: SSPC-SP10/NACE 2

System Tested*:

- 1 ct. Zinc Clad III HS @ 5.0 mils (125 microns) dft
- 1 ct. Macropoxy 646 @ 5.0-10.0 mils (125-250 microns) dft
- 1 ct. Acronol 218 HS @ 5.0 mils (125 microns) dft

*unless otherwise noted below

Test Name	Test Method	Results
Adhesion	ASTM D4541	1976 psi
Corrosion Weathering	ASTM D5894, 27 cycles, 9072 hours	Rating 10 per ASTM D610 for rusting. Rating 10 per ASTM D714 for blistering
Dry Heat Resistance (zinc only)	ASTM D2485	400°F (204°C)
Moisture Condensation Resistance	ASTM D4585, 100°F (38°C), 4000 hours	Rating 10 per ASTM D610 for rusting. Rating 10 per ASTM D714 for blistering
Pencil Hardness (zinc only)	ASTM D3363	2H
Salt Fog Resistance	ASTM B117, 15,000 hours	Rating 10 per ASTM D610 for rusting. Rating 10 per ASTM D714 for blistering
Slip Coefficient* (zinc only)	AISC Specifications for Structural Joints using ASTM A325 or ASTM A490 Bolts	Class B, 0.52
Slip Coefficient* ¹	AISC Specification for Structural Joints using ASTM A325 or ASTM A490 Bolts	Passes Class B, 0.58

Meets SSPC Paint Spec 20 - 1ct. Zinc @ 5 mils (125 microns) dft

Complies with ISO 12944-5 C5I and C5M requirements.

Footnotes:

¹ 1 ct. Zinc Clad III HS @ 3.0-5.0 mils (75-125 microns) dft

² 1 ct. Steel Spec Epoxy Primer @ 4.0-6.0 mils (100-150 microns) dft

³ Refer to Slip Certification document



Protective & Marine Coatings

Revised: August 04, 2016

ZINC CLAD® III HS ORGANIC ZINC-RICH EPOXY PRIMER

PART A	B69A100	GRAY-GREEN, BASE
PART A	B69LW100	OAP BLUE, BASE
PART B	B69V100	HARDENER
PART F	B69D11	ZINC DUST

PRODUCT INFORMATION

6.07

RECOMMENDED SYSTEMS

		Dry Film Thickness / ct Mils (Microns)
Steel, polyurethane topcoat:		
1 ct. Zinc Clad III HS	3.0-5.0	(75-125)
1-2 cts. Acrolon 218 HS	3.0-6.0	(75-150)
Steel, catalyzed epoxy topcoat:		
1 ct. Zinc Clad III HS	3.0-5.0	(75-125)
1-2 cts. Macropoxy 646	5.0-10.0	(125-250)
Steel, catalyzed epoxy topcoat:		
1 ct. Zinc Clad III HS	3.0-5.0	(75-125)
1-2 cts. Tile-Clad HS	2.5-4.0	(63-100)
Steel, catalyzed epoxy siloxane topcoat:		
1 ct. Zinc Clad III HS	3.0-5.0	(75-125)
1-2 cts. Polysiloxane XLE-80	3.0-7.0	(75-175)
or		
1-2 cts. Polysiloxane XLE-80 HAPS Free	3.0-7.0	(75-175)
Steel, acrylic topcoat:		
1 ct. Zinc Clad III HS	3.0-5.0	(75-125)
2 cts. Pro Industrial DTM Acrylic Coating	2.5-4.0	(63-100)
or		
1 ct. Fast Clad HB Acrylic	5.0-8.0	(125-200)
Steel, water based epoxy topcoat:		
1 ct. Zinc Clad III HS	3.0-5.0	(75-125)
2 cts. Waterbased Tile-Clad Epoxy	2.0-4.0	(50-100)
Steel, water-based urethane topcoat:		
1 ct. Zinc Clad III HS	3.0-5.0	(75-125)
1 ct. Waterbased Tile-Clad Epoxy	2.0-4.0	(50-100)
1-2 cts. Hydrogloss	2.0-4.0	(50-100)
Steel, Class B Compliant System:		
1 ct. Zinc Clad III HS	3.0-5.0	(75-125)
1 ct. Steel Spec Epoxy Primer (red)	4.0-6.0	(100-150)
ISO 12944 C5M System:		
1 ct. Zinc Clad III HS	3.0-5.0	(75-125)
1 ct. Fast Clad Urethane	6.0-9.0	(150-225)
or		
1 ct. Zinc Clad III HS	3.0-5.0	(75-125)
1 ct. Tower Guard Epoxy	5.0-11.5	(125-287.5)
1 ct. Acrolon 218 HS	3.0-6.0	(75-150)

FIRETEX ONLY

Steel Substrate being primed for FIRETEX M90 and M90/2
1 ct. Zinc Clad III HS 3.0-6.0 (75-150)

The systems listed above are representative of the product's use, other systems may be appropriate.

DISCLAIMER

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Information and Application Bulletin.

SURFACE PREPARATION

Surface must be clean, dry, and in sound condition. Remove all oil, dust, grease, dirt, loose rust, and other foreign material to ensure adequate adhesion.

Refer to product Application Bulletin for detailed surface preparation information.

Minimum recommended surface preparation:

Iron & Steel:	SSPC-SP6/NACE 3, 2 mil (50 micron) profile
---------------	--

Galvanizing:	SSPC-SP7
--------------	----------

Weathered Zinc Rich Primer:	Clean, dry, sound
-----------------------------	-------------------

Surface Preparation Standards

Condition of Surface	ISO 8501-1 BS7079:A1	SSPC	NACE
White Metal	Sa 3	SP 5	1
Near White Metal	Sa 2.5	SP 10	2
Commercial Blast	Sa 2	SP 6	3
Brush-Off Blast	Sa 1	SP 7	4
Hand Tool Cleaning	Rusted CSt 2	SP 2	-
	Pitted & Rusted DSt 2	SP 2	-
Power Tool Cleaning	Rusted CSt 3	SP 3	-
	Pitted & Rusted DSt 3	SP 3	-

TINTING

Do not tint.

APPLICATION CONDITIONS

Temperature: 35°F (1.7°C) minimum, 120°F (49°C) maximum (air and surface)
40°F (4.5°C) minimum, 120°F (49°C) maximum (material)

Relative humidity: At least 5°F (2.8°C) above dew point 85% maximum

Refer to product Application Bulletin for detailed application information.

ORDERING INFORMATION

Packaging:

3.25 gallons (12.3L) mixed:

Part A	1 gallon (3.78L)
Part B	1 gallon (3.78L)
Part F	73 lb (33 Kg) Zinc Dust

1 gallon (3.78L) mixed:

Part A	0.30 gallon (1.14L)
Part B	0.30 gallon (1.14L)
Part F	22 lb (10 Kg) Zinc Dust

Weight: 27.63 ± 0.2 lb/gal ; 3.31 Kg/L, mixed

SAFETY PRECAUTIONS

Refer to the MSDS sheet before use.

Published technical data and instructions are subject to change without notice. Contact your Sherwin-Williams representative for additional technical data and instructions.

WARRANTY

The Sherwin-Williams Company warrants our products to be free of manufacturing defects in accord with applicable Sherwin-Williams quality control procedures. Liability for products proven defective, if any, is limited to replacement of the defective product or the refund of the purchase price paid for the defective product as determined by Sherwin-Williams. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY SHERWIN-WILLIAMS, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.



Protective & Marine Coatings

Revised: August 04, 2016

ZINC CLAD® III HS ORGANIC ZINC-RICH EPOXY PRIMER

PART A	B69A100	GRAY-GREEN, BASE
PART A	B69LW100	OAP BLUE, BASE
PART B	B69V100	HARDENER
PART F	B69D11	ZINC DUST

APPLICATION BULLETIN

6.07

SURFACE PREPARATIONS

Surface must be clean, dry, and in sound condition. Remove all oil, dust, grease, dirt, loose rust, and other foreign material to ensure adequate adhesion.

Zinc rich coatings require direct contact between the zinc pigment in the coating and the metal substrate for optimum performance.

Iron & Steel (atmospheric service)

Remove all oil and grease from surface by Solvent Cleaning per SSPC-SP1. Minimum surface preparation is Commercial Blast Cleaning per SSPC-SP6/NACE 3. For better performance, use Near White Metal Blast Cleaning per SSPC-SP10/NACE 2. Blast clean all surfaces using a sharp, angular abrasive for optimum surface profile (2 mils / 50 microns). Coat any bare steel the same day as it is cleaned or before flash rusting occurs.

When used on Ductile Iron Pipe, surface preparation shall be in accordance with NAPF 500-03-04 Abrasive Blast Cleaning of Ductile Iron Pipe with a minimum 1.0 mil surface profile.

Galvanized Steel

Allow to weather a minimum of six months prior to coating. Solvent Clean per SSPC-SP1 (recommended solvent is VM&P Naphtha). When weathering is not possible, or the surface has been treated with chromates or silicates, first Solvent Clean per SSPC-SP1 and apply a test patch. Allow paint to dry at least one week before testing adhesion. If adhesion is poor, brush blasting per SSPC-SP7 is necessary to remove these treatments. Rusty galvanizing requires a minimum of Hand Tool Cleaning per SSPC-SP2, prime the area the same day as cleaned or before flash rusting occurs.

Weathered Zinc-Rich Primer

Remove zinc salts by either high pressure water washing and scrubbing with stiff bristle brush or sweep blast followed by water flush. Allow to dry.

Note: If blast cleaning with steel media is used, an appropriate amount of steel grit blast media may be incorporated into the work mix to render a dense, angular 1.5-3.0 mil (38-75 micron) surface profile, per Keane-Tator Surface Profile Comparator. A profile up to 4 mils (100 microns) is acceptable, however, coating must be applied to achieve a minimum of 3 mils (75 microns) dft. This method may result in improved adhesion and performance.

Surface Preparation Standards					
Condition of Surface	ISO 8501-1 BS7079: A1	Swedish Std. SI5055900	SSPC	NACE	
White Metal	Sa 3	Sa 3	SP 5	1	
Near White Metal	Sa 2.5	Sa 2.5	SP 10	2	
Commercial Blast	Sa 2	Sa 2	SP 6	3	
Brush-Off Blast	Sa 1	Sa 1	SP 7	4	
Hand Tool Cleaning	Rusted	C St 2	C St 2		
	Pitted & Rusted	D St 2	D St 2	SP 2	-
	Rusted	C St 3	C St 3	SP 3	-
Power Tool Cleaning	Pitted & Rusted	D St 3	D St 3	SP 3	-

APPLICATION CONDITIONS

Temperature: 35°F (1.7°C) minimum, 120°F (49°C) maximum (air and surface)
40°F (4.5°C) minimum, 120°F (49°C) maximum (material)
At least 5°F (2.8°C) above dew point

Relative humidity: 85% maximum

APPLICATION EQUIPMENT

The following is a guide. Changes in pressures and tip sizes may be needed for proper spray characteristics. Always purge spray equipment before use with listed reducer. Any reduction must be compliant with existing VOC regulations and compatible with the existing environmental and application conditions.

Reducer/Clean Up

Below 80°F	Reducer #58 or MEK, R6K10
Above 80°F	Reducer #58 or R7K104

Airless Spray

(use Teflon packings and continuous agitation)

Pressure	2000 - 2300 psi
Hose	3/8" ID
Tip	.019"
Filter	none
Reduction	As needed up to 5% by volume

Conventional Spray

(continuous agitation required)

Gun	Binks 95
Fluid Nozzle	68
Air Nozzle	68P
Atomization Pressure	50 psi
Fluid Pressure	10 - 20 psi
Reduction	As needed up to 5% by volume

Keep pressure pot at level of applicator to avoid blocking of fluid line due to weight of material. Blow back coating in fluid line at intermittent shutdowns, but continue agitation at pressure pot.

Brush

Brush	Small areas only; natural bristle
Reduction	Not recommended

If specific application equipment is not listed above, equivalent equipment may be substituted.



Protective & Marine Coatings

ZINC CLAD® III HS ORGANIC ZINC-RICH EPOXY PRIMER

PART A	B69A100	GRAY-GREEN, BASE
PART A	B69LW100	OAP BLUE, BASE
PART B	B69V100	HARDENER
PART F	B69D11	ZINC DUST

Revised: August 04, 2016

APPLICATION BULLETIN

6.07

APPLICATION PROCEDURES

Surface preparation must be completed as indicated.

Zinc Clad III HS comes in 3 premeasured containers which when mixed provides 3.25 gallons (12.3L) of ready-to-apply material.

Mixing Instructions:

Mix contents of component A and B thoroughly with low speed power agitator. Make certain no pigment remains on the bottom of the can. Then combine 1 part by volume of Part A with 1 part by volume of Part B, then add Part F (73 lb zinc dust). Thoroughly agitate the mixture with power agitation. After mixing, pour through a 30-60 mesh screen. Allow the material to sweat-in as indicated. Re-stir before using.

If reducer solvent is used, add only after components have been thoroughly mixed, after sweat-in.

Continuous agitation of mixture during application is required, otherwise zinc dust will quickly settle out.

Apply paint at the recommended film thickness and spreading rate as indicated below:

Recommended Spreading Rate per coat:

	Minimum	Maximum
Wet mils (microns)	4.5 (113)	7.0 (175)
Dry mils (microns)	3.0 (75)	5.0 (125)
~Coverage sq ft/gal (m²/L)	224 (5.5)	370 (9.1)
Theoretical coverage sq ft/gal (m²/L) @ 1 mil / 25 microns dft	1120 (27.5)	

NOTE: Brush or roll application may require multiple coats to achieve maximum film thickness and uniformity of appearance.

Drying Schedule @ 5.0 mils wet (125 microns):

@ 35°F/1.7°C @ 77°F/25°C @ 120°F/49°C

50% RH

To touch:	45 minutes	30 minutes	10 minutes
To handle:	2 hours	1 hour	30 minutes
To recoat*:			
minimum:	4 hours	30 minutes	30 minutes
**maximum:	none	none	none
To cure:	10 days	7 days	7 days

Drying time is temperature, humidity, and film thickness dependent.

*NOTE: Film must be free of solvent, hard and firm. When rubbed with the face of a coin or knife the film should polish but not flake or chip.

**Maximum Recoat Unlimited Must have a clean, dry surface for top-coating. "Loose" chalk or salts must be removed in accordance with good painting practice.

Paint temperature must be at least 40°F (4.5°C) minimum.

Pot Life: 6 hours 4 hours 2 hours

Sweat-in-Time: 1 hour 30 minutes 15 minutes

Application of coating above maximum or below minimum recommended spreading rate may adversely affect coating performance.

CLEAN UP INSTRUCTIONS

Clean spills and splatters immediately with MEK, R6K10. Clean tools immediately after use with MEK, R6K10. Follow manufacturer's safety recommendations when using any solvent.

DISCLAIMER

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Information and Application Bulletin.

PERFORMANCE TIPS

Stripe coat all crevices, welds, and sharp angles to prevent early failure in these areas.

When using spray application, use a 50% overlap with each pass of the gun to avoid holidays, bare areas, and pinholes. If necessary, cross spray at a right angle.

Spreading rates are calculated on volume solids and do not include an application loss factor due to surface profile, roughness or porosity of the surface, skill and technique of the applicator, method of application, various surface irregularities, material lost during mixing, spillage, overthinning, climatic conditions, and excessive film build.

Excessive reduction of material can affect film build, appearance, and performance.

Do not mix previously catalyzed material with new.

Do not apply the material beyond recommended pot life.

In order to avoid blockage of spray equipment, clean equipment before use or before periods of extended downtime with MEK, R6K10.

Keep pressure pot at level of applicator to avoid blocking of fluid line due to weight of material. Blow back coating in fluid line at intermittent shutdowns, but continue agitation at pressure pot.

SSPC-SP11 surface preparation is acceptable for small areas.

Higher dry film thickness may be acceptable under certain conditions. Contact your Sherwin-Williams representative.

Refer to Product Information sheet for additional performance characteristics and properties.

SAFETY PRECAUTIONS


Refer to the MSDS sheet before use.

Published technical data and instructions are subject to change without notice. Contact your Sherwin-Williams representative for additional technical data and instructions.


WARRANTY

The Sherwin-Williams Company warrants our products to be free of manufacturing defects in accord with applicable Sherwin-Williams quality control procedures. Liability for products proven defective, if any, is limited to replacement of the defective product or the refund of the purchase price paid for the defective product as determined by Sherwin-Williams. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY SHERWIN-WILLIAMS, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.


12 PCS
PRIMED



#6




B



#6

18 PCS
PRIMED




#3A


16 PCS
PRIMED

14"

20 PCS
PRIMED



8 PCS
PRIMED



12 PCS
PRIMED

